The Structure of the Metallic Quarternary Phase ZrTaNO

NILS SCHÖNBERG

Institute of Chemistry, University of Uppsala, Uppsala, Sweden

The structures and approximate compositions of the binary metallic phases in the Zr—N, Zr—O, Ta—N, and Ta—O systems are known. The present author has recently published a study of the metallic corner of the Ta—N—O system, where four ternary phases were found¹. Zr—N—O samples with the (N, O)/Zr ratio ≤ 1 were also prepared. The results obtained indicate a solid solubility of nitrogen and oxygen in the α -Zr lattice up to the approximate limit $\text{Zr}_2(\text{N}, \text{O})$, as well as that a continuous solid solution series ZrN—ZrO exists*./

The products were investigated by taking X-ray powder photographs in a focussing camera of Guinier type using monochromatized Cu- $K\alpha$ radiation.

Powdered ZrTa alloys with the compositions $\text{ZrTa}_{0.33}$, $\text{ZrTa}_{0.67}$, ZrTa , $\text{Zr}_{0.67}\text{Ta}$, $\text{Zr}_{0.33}\text{Ta}$ were used as starting materials for the preparation of ternary nitrides and oxides and quarternary nitride-oxides. These alloys were obtained by heating zirconium hydride and tantalum hydride (both from Metal Hydride Inc.) in zirconia crucibles in a high frequency vacuum induction furnace² at a temperature of about 1700°C. Ammonia nitriding with oxygen-free dry ammonia at various temperatures between 700°C and 1100°C caused the formation of binary nitride phases. Analogously, binary oxide phases were formed, when the samples were oxidized with steam in the presence of hydrogen in great excess at a temperature of 700°C.

When a mixture of steam and ammonia (in great excess) was passed over the alloys at 700°C a new phase was formed. It was obtained in a fairly pure state (traces of ZrO_2 as impurity) starting with the sample of the composition ZrTa and after a reaction time of about three hours. The formula of this compound may thus be written $\text{ZrTa}_x\text{N}_x\text{O}_y$. The presence of hydrogen in the lattice is most unlikely, as heating *in vacuo* at 1100°C for one hour did not cause any structural change. The nitrogen content was determined by the Kjeldahl method. The oxygen content was determined indirectly by weighing the ZrO_2 and Ta_2O_5 formed after oxidation of the specimen with oxygen.

* Published data on the lattice constants of ZrN differ considerably. The results obtained by the present author are therefore reported here. The cube-edge of the ZrN phase was found to be $a = 4.537\text{—}4.562$ Å and that of the ZrO phase $a = 4.584\text{—}4.620$ Å. The high value of $a = 4.63$ Å for zirconium nitride given by some authors is most likely due to the presence of oxygen in the lattice. Both phases have broad homogeneity ranges, approximately 10 atom-%.

Table 1. Calculated and observed intensities for the ZrTaNO phase.

<i>hkl</i>	<i>I</i> _{calc.}	<i>I</i> _{obs.}
0,0,1	40	50
1,0,0	224	250
1,0,1	251	250
0,0,2	69	75
1,1,0	184	160
1,0,2	96	110
1,1,1	32	35
2,0,0	46	50
2,0,1	199	160
1,1,2	235	250
0,0,3	4	0
2,0,2	63	75
1,0,3	128	110
2,1,0	55	50
2,1,1	229	250
1,1,3	16	15
3,0,0	67	75
2,1,2	86	75
3,0,1	16	15

<i>hkl</i>	<i>I</i> _{calc.}	<i>I</i> _{obs.}
2,0,3	98	110
0,0,4	18	15
1,0,4	76	75
3,0,2	97	110
2,2,0	48	50
2,2,1	12	15
2,1,3	148	160
3,1,0	33	35
1,1,4	102	110
3,1,1	155	160
2,0,4	41	35
2,2,2	114	110
3,0,3	19	15
3,1,2	121	110

Because of the unfavourable weight ratio $y\text{O}/\text{ZrTaN}_x\text{O}_y$, this method gives only an approximate value for y . The results closely corresponded to $x = y = 1$, however, corresponding to the ideal formula ZrTaNO . The phase has a greyish black metallic lustre.

From powder photograph interpretation the unit cell was found to have hexagonal symmetry with the lattice constants $a = 3.645 \text{ \AA}$, $c = 3.881 \text{ \AA}$, $c/a = 1.065$ ($V = 44.66 \text{ \AA}^3$). The calculated density for one formula unit ZrTaNO is 11.24. The observed value was 10.6. The Zr and Ta atoms occupy ordered positions in an arrangement of hexagonal close-packing. This is evident from Table 1, where the observed intensities are compared with the intensities calculated for this case.

Each metal atom is surrounded by six metal atoms of the same kind at a distance of $3.645 \text{ \AA}$ and six metal atoms of the other kind at a distance of $2.863 \text{ \AA}$. For 12-coordination of atoms Pauling gives the radius values: $r_{\text{Zr}} = 1.60 \text{ \AA}$ and $r_{\text{Ta}} = 1.49 \text{ \AA}$; $r_{\text{Zr}} + r_{\text{Ta}} = 3.09 \text{ \AA}$. As the mean interatomic distances are $3.25 \text{ \AA}$, these are 5 % greater than those given for the pure metals for the same coordination number. This is in agreement with the corresponding increase of metal-metal distances for most metallic carbides, nitrides, and oxides of "interstitial" structure types.

At first sight the nonmetal atoms would be expected to be situated at the centres of metal atom octahedra, *i.e.* in the positions $2/3, 1/3, 1/4$ and $2/3, 1/3, 3/4$, if the Zr and Ta atoms occupy the positions $0,0,0$ and $1/3, 2/3, 1/2$, respectively, as this configuration is typical for nitrides and oxides with metallic character. Each nonmetal atom would then be surrounded by six metal and two nonmetal atoms at distances of $2.32 \text{ \AA}$ and $1.94 \text{ \AA}$ respectively. However, the observed

N—N, O—O, and N—O distances *always* exceed the value 2.5 Å in the compounds mentioned above. This can be explained by a displacement of electrons from the transition metal to the nonmetal atom, so that the metal-nonmetal bonds have a partial ionic character. If the N—O distances are accordingly assumed to be greater than 2.5 Å, the only possible placing is with the nonmetal atoms in the positions $1/3, 2/3, 0$ and $2/3, 1/3, 1/2$. The resulting N—O distances are 2.863 Å (6-coordination). From space considerations and from the consideration that the metal-oxygen bonds are stronger than the metal-nitrogen bonds, the oxygen atom is most likely to be in the position $1/3, 2/3, 0$ and the nitrogen atom in $2/3, 1/3, 1/2$. The oxygen atom in this arrangement is at the centre of a bipyramid of 3 Zr and 2 Ta atoms, and the nitrogen atom has a triangle of 3 Ta atoms around it, in the same plane.

The interatomic Zr—Zr and Ta—Ta distances are so great — 3.645 Å — that the metal atoms can be considered to have 6-coordination: the Zr—Ta distances are 2.863 Å. If Pauling's correction factor for 6-coordination is used in this case, assuming that the Born exponent $n \sim 9^3$, the resulting atomic radii are: $r_{\text{Zr}} = 1.47$ Å, $r_{\text{Ta}} = 1.37$ Å; $r_{\text{Zr}} + r_{\text{Ta}} = 2.84$ Å. This value is in good agreement with the observed one, 2.86 Å. The O—Zr (3 atoms), O—Ta (2 atoms), and N—Ta (3 atoms) distances are 2.11 Å, 1.94 Å, and 2.11 Å respectively. The calculated radius value for the O atom is then 0.64 Å and 0.57 Å, and that for the N atom 0.74 Å, closely corresponding to the radii given by Goldschmidt and Pauling: 0.60 Å and 0.71 Å respectively.

In the structure suggested here, the configurations of the Zr—Ta and O—N lattices are identical. The lattices are displaced $1/3, 2/3, 0$ from each other. The space-group is D_{3d}^1 — $P\bar{6}m2$ with the following atomic positions: 1 Zr in 1 (a) 0,0,0, 1 Ta in 1 (d) $1/3, 2/3, 1/2$; 1 O in 1 (c) $1/3, 2/3, 0$, and 1 N in 1 (f) $2/3, 1/3, 1/2$.

SUMMARY

Some sections of the quaternary Zr—Ta—N—O system have been investigated by X-ray methods to find whether metallic ternary and quaternary phases exist.

A metallic compound ZrTaNO has been prepared. The metal atoms occupy ordered positions in a hexagonal close-packed arrangement. The c/a value is close to unity, differing widely from the ideal value of $\sqrt{8/3} = 1.63$. The positions of the nonmetal atoms have been discussed. A structure is suggested which is not related to that of metallic compounds of "interstitial" structure types.

The author wishes to express his gratitude to Professor G. Hägg for his never-failing interest. A grant from *Statens Tekniska Forskningsråd* is gratefully acknowledged.

REFERENCES

1. Schönberg, N. *Acta Chem. Scand.* **8** (1954) 620.
2. Kiessling, R. *Jernkontorets Ann.* **132** (1948) 237.
3. Pauling, L. *Nature of the chemical bond*, London 1948, Chapters X and XI.

Received January 21, 1954.